


Framework Type Data



framework viewed along [010]


Idealized cell data: orthorhombic, *Pnma*, $a = 20.1\text{\AA}$, $b = 19.7\text{\AA}$, $c = 13.1\text{\AA}$

Coordination sequences and vertex symbols:

see Appendix A for a list of the coordination sequences and vertex symbols for the 12 T-atoms

Secondary building units: 5-1

Composite building units:



Materials with this framework type:

*ZSM-5⁽¹⁻³⁾

[As-Si-O]-MFI⁽⁴⁾

[Fe-Si-O]-MFI⁽⁵⁾

[Ga-Si-O]-MFI⁽⁶⁾

AMS-1B⁽⁷⁾

AZ-1⁽⁸⁾

Bor-C⁽⁹⁾

Boralite C⁽¹⁰⁾

Encilite⁽¹¹⁾

FZ-1⁽¹²⁾

LZ-105⁽¹³⁾

Monoclinic H-ZSM-5⁽¹⁴⁾

Mutinaite⁽¹⁵⁾

NU-4⁽¹⁶⁾

NU-5⁽¹⁷⁾

Silicalite⁽¹⁸⁾

TS-1⁽¹⁹⁾

TSZ⁽²⁰⁾

TSZ-III⁽²¹⁾

TZ-01⁽²²⁾

USC-4⁽²³⁾

USI-108⁽²⁴⁾

ZBH⁽²⁵⁾

ZKQ-1B⁽²⁶⁾

ZMQ-TB⁽²⁷⁾

organic-free ZSM-5⁽²⁸⁾


Type Material: ZSM-5

Type Material Data



Crystal chemical data: $\text{[Na}_n(\text{H}_2\text{O})_{16}\text{] [Al}_n\text{Si}_{96-n}\text{O}_{192}\text{]-MFI}$, $n < 27$
orthorhombic, $Pnma$, $a = 20.07\text{\AA}$, $b = 19.92\text{\AA}$, $c = 13.42\text{\AA}$ ⁽²⁾

Framework density: 17.9 T/1000 \AA^3

Channels: $\{[100] \mathbf{10} \ 5.1 \times 5.5 \leftrightarrow [010] \mathbf{10} \ 5.3 \times 5.6\}^{***}$



10-ring viewed along [100]



10-ring viewed along [010]

References:

- (1) Kokotailo, G.T., Lawton, S.L., Olson, D.H. and Meier, W.M. *Nature*, **272**, 437-438 (1978)
- (2) Olson, D.H., Kokotailo, G.T., Lawton, S.L. and Meier, W.M. *J. Phys. Chem.*, **85**, 2238-2243 (1981)
- (3) van Koningsveld, H., van Bekkum, H. and Jansen, J.C. *Acta Crystallogr.*, **B43**, 127-132 (1987)
- (4) Bhaumik, A. and Kumar, R. *Chem. Commun.*, 869-870 (1995)
- (5) Patarin, J., Kessler, H. and Guth, J.L. *Zeolites*, **10**, 674-679 (1990)
- (6) Awate, S.V., Joshi, P.N., Shiralkar, V.P. and Kotasthane, A.N. *J. Incl. Phenom.*, **13**, 207-218 (1992)
- (7) Klotz, M.R. *U.S. Patent 4,269,813* (1981)
- (8) Chono, M. and Ishida, H. *E. Patent B-113,116* (1984)
- (9) Taramasso, M., Perego, G. and Notari, B. *Proc. 5th Int. Zeolite Conf.*, pp. 40-48 (1980)
- (10) Taramasso, M., Manara, G., Fattore, V. and Notari, B. *GB Patent 2,024,790* (1980)
- (11) Ratnasamy, P. and Borade, M.B. *E. Patent A-160,136* (1985)
- (12) Suzuki, T., Hashimoto, S. and Nakano, R. *E. Patent B-31,255* (1981)
- (13) Grose, R.W. and Flanigen, E.M. *U.S. Patent 4,257,885* (1981)
- (14) van Koningsveld, H., Jansen, J.C. and van Bekkum, H. *Zeolites*, **10**, 235-242 (1990)
- (15) Vezzalini, G., Quartieri, S., Galli, E., Alberti, A., Cruciani, G. and Kvick, A. *Zeolites*, **19**, 323-325 (1997)
- (16) Whittam, T.V. *E. Patent B-65,401* (1986)
- (17) Whittam, T.V. *E. Patent B-54,386* (1982)
- (18) Flanigen, E.M., Bennett, J.M., Grose, R.W., Cohen, J.P., Patton, R.L., Kirchner, R.M. and Smith, J.V. *Nature*, **271**, 512-516 (1978)
- (19) Taramasso, M., Perego, G. and Notari, B. *U.S. Patent 4,410,501* (1983)
- (20) Ashibe, K., Kobayashi, W., Maejima, T., Sakurada, S. and Tagaya, N. *E. Patent A-101,232* (1984)
- (21) Sakurada, S., Tagaya, N., Miura, T., Maeshima, T. and Hashimoto, T. *E. Patent A-170,751* (1986)
- (22) Iwayama, K., Kamano, T., Tada, K. and Inoue, T. *E. Patent A-57,016* (1982)
- (23) Young, D.A. *U.S. Patent 4,325,929* (1982)
- (24) Hinnenkamp, J.A. and Walatka, V.V. *U.S. Patent 4,423,020* (1983)
- (25) Holderich, W., Mross, W.D. and Schwartzmann, M. *E. Patent B-77,946* (1986)
- (26) Kee Kwee, L.S.L. *E. Patent A-148,038* (1984)
- (27) Kee Kwee, L.S.L. *E. Patent A-104,107* (1983)
- (28) Kim, S.D., Noh, S.H., Seong, K.H. and Kim, W.J. *Microporous Mesoporous Mat.*, **72**, 185-192 (2004)